



KOLIBIR LTD – Road marking paint

KOLPLAST 860

Red 3K COLD PLASTIC MATERIAL

Suitable for road marking system.

TECHNICAL BULLETIN

CHRACTERISTIC	TEST METHOD	REQUIREMENT	RESULT
DRYING TIME	UNE 135202	$t \leq 30$	$t \leq 30$
COLOR	IS 1871	X,Y COORDINATES WITHIN THE POLYGON	X,Y COORDINATES WITHIN THE POLYGON
LUMINANCE FACTOR β	IS 1871	$\beta \geq 0.12$	$\beta = 0.16$
STORAGE STABILITY	IS 1871	A RATING OF MIN. 3	A RATING OF 8
UV AGEING	IS 1871	X,Y COORDINATES WITHIN THE POLYGON $\Delta\beta \leq 0.05$	X,Y COORDINATES WITHIN THE POLYGON CLASS UV1 $\Delta\beta = 0.01$
ALKALI RESISTANCE	IS 1871	NO CHANGE OF THE FILM SURFACE	NO CHANGE OF THE FILM SURFACE
SKID RESISTANCE	IS 1871	$S2 \geq 50$ at P7	$S2 = 53$ at P7

Data presented here are based on our best knowledge and experience, we reserve the right to update and/or alter it without prior notice

KOLIBIR LTD 5 Modeine st. Petach-Tikva 4927154 ISRAEL

info@kolibir.co.il www.kolibir.com addition 06/2017