KOLIBIR LTD – Road marking paint

Kol-Cryl Blue 660 , Black 670 , Red 680 - USE DIRECTIONS

Type blue 660 , Black 670 , Red 680 are a solvent based Acrylic paints , intended to mark asphalt and concrete roads.
The paint is suitable for use , according to Israeli standard (IS) 1871.

Preparation of the road surface

The asphalt/concrete surface has to be in good condition and according to the relevant standard.
The surface quality has great influence on the performance of the paint.
Do not paint on wet or humid surface, or 7 days before rainfall. The surface has to be clean, without any leftovers of dust, oil, grease or sand.
New surfaces have to be at least 6 weeks old. When painting new asphalt, a temporary layer has to be applied at first, to prevent bleeding.
When painting new concrete, extra care has to be taken, to remove all strange materials (materials such as sealants etc..).
Concrete which has been smoothed, the surface has to be roughened up, to enhance paint adhesion.
The paint can be applied on old Alkyd, Acrylic, Thermoplastic, or Cold plastic paints, but the adhesion of the old paint to the surface has to be checked, do not paint on loose paint.

Environmental conditions

Temperature: 10°c-40°c.
Surface temperature: at least 3C° above the dew point.
Relative humidity: 80% max.
Wind speed: below 25 Km/hour.

Application:

Apply with brush or airless spry, preferably with a special airless for road marking.
The paint has to be mixed well before use.

KOLIBIR LTD – Road marking paint

Kol-Cryl Blue 660 , Black 670 , Red 680 - USE DIRECTIONS

Drying:

The paint has to be protected from traffic until is completely dry.

Drying time – less then 30 min. at 25°c.

Dilution:

If necessary use up to 3% Toluene, or road marking thinner, made by Kolibir.

Quantity:

Approx. 36 square meters per 18L gallon.

Coverage:

The hiding power is influenced by the application system and it's quality, by the depth of the road structure and the weather.

Storage:

Shelf life – 1 year.

The paint has to be stored in a shaded place, extreme temperature have to be avoided, the paint has to be stored with the appropriate carefulness and according to it's safety data sheet.

The paint is produced under a strict quality control procedure.

Data presented here is based on our best knowledge and experience, we reserve the right to update and/or alter it without prior notice.

KOLIBIR LTD 5 Modeine st. Petach-Tikva 4927154 ISRAEL Tel: 97239046652 Fax: 97239046452

info@kolibir.co.il www.kolibir.com