



Kolibir Ltd.

קוליביר בע"מ

Use directions : Yellow road marking paint

Cat. no. 605

Coverage: 36 square meters per 18 liter container.

Thinning: max. 10% with road marking thinner produced by Kolibir Ltd.

Cleaning: road marking thinner by Kolibir Ltd.

Storage: 12 month in originally closed container.

Application: spaying , brushing at:

temperature 10-40 deg. Celsius

relative humidity: max. 65%

To achieve good marking of the road , the Israeli standard 934 has to be observed.

The paint must be mixed to homogeny liquid.

The road has to be cleaned from dust and dirt, don't paint a wet road or 7 days before rain.

When night time visibility is required , use glass beads according to I.S 1423 Potters 125-600T.

Quantities: apply 800 gr. Paint and 350 gr. Glass beads per square meter

The quantities apply to a structure of 0.1-0.7 mm depth.

The glass beads have to be applied on the wet paint immediately after paint application.

Version : 12-2013

www.kolibir.com

info@kolibir.com